DUVILAX[®] BD-50/59

Properties

Homopolymeric polyvinyl acetate dispersion in the aqueous environment containing an external plasticiser. The emulsion system consists of a non-ionic emulsifier and polyvinyl alcohol as a protective colloid. It is biodegradable.

Application

Duvilax BD-50/59 is a special dispersive adhesive applied for glueing in polygraphy, above all, for glueing of book blocks spines. It is used without dilution or other treatments. Duvilax BD-50/59 may be applied for glueing materials coming into contact with food.

Parameters

| appearance | viscous liquid of white colour |
|------------------------------|---|
| dry matter content | min. 58,0 % |
| viscosity | 5 000 – 13 000 mPa.s (Rheotest) 5 000 –50 000 mPa.s (Brookfield RVT, ISO 2555) |
| Н | 3 - 7 |
| nin.film forming temperature | 0 °C |
| film properties | transparent, elastic, soft and sticky |
| | |

Storage

Duvilax BD-50/59 is stored in the original, undamaged and closed containers, at the temperature ranging from 5°C to 40°C; it must not be exposed to direct sunlight. Goods delivered in cisterns are stored in specially designed reservoirs protected against corrosion due to the effect of the slightly acid environment. Free access of air from the surrounding environment needs to be prevented in reservoirs (for example via a water valve) or reservoirs need to be equipped with an agitator. Avoid mixing with other agents and micro-biologically defective material. After emptying a reservoir, the reservoir needs to be cleaned and disinfected with a biocidal agent.

Packaging

plastic packages: 30kg keg, 125kg; steel barrel 200kg, 220kg; plastic container 1,000kg; rail and car tank.

Warranty

6 months from the date of production if storage conditions are observed.

Updated: 05/2017

This technical data sheet cancels all previous versions and replaces them. Information contained therein are not binding and are only of an informative and general character. They are based on our own experience, research and objective testing. The product meets the above specifications only during the warranty period and under the conditions in this data sheet. The company Duslo, Inc. does not guarantee the suitability of the product for a particular purpose. Use of the product for a specific purpose, including suitability for a particular purpose and methods of its use, is the customer obliged to test in specific technology conditions. Information relating to health and safety at work are provided in the Material Safety Data Sheet. More product information, details and contacts are available on www.duslo.sk. Written and / or oral advice, relating to a product, has the character of a non-binding recommendation.



Duslo, a.s. Administratívna budova ev. č. 1236 927 03 Šaľa Slovenská republika TEL. +421 31 775 2266 +421 31 775 3064 +421 31 775 4391

E-MAIL WEB

duvilax@duslo.sk www.duslo.sk www.duvilax.sk